

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 985 558 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

15.03.2000 Bulletin 2000/11

(51) Int Cl.7: B60C 17/00, B60C 13/00

(21) Application number: 99307078.8

(22) Date of filing: 07.09.1999

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 08.09.1998 JP 25424398

(71) Applicant: SUMITOMO RUBBER INDUSTRIES,
LTD.

Hyogo-ken (JP)

(72) Inventor: Yoshioka, Tetsuhiko

Kobe-shi, Hyogo-ken (JP)

(74) Representative: Stewart, Charles Geoffrey

Technical,

Dunlop Tyres Ltd.,

Fort Dunlop

Erdington, Birmingham B24 9QT (GB)


Remarks:

The application is published incomplete as filed
(Article 93 (2) EPC).

(54) Run-flat tyre

(57) A run-flat tyre comprises a carcass (6) composed of an inner ply (6A) and an outer ply (6B) each made of organic fibre cords, a belt (7) disposed radially outside the carcass (6) in the tread portion (2), and three sidewall reinforcing rubber layers (9a, 9b, 9c) disposed in each sidewall portion. The inner and outer carcass plies are turned up around the bead cores (5) from the inside to the outside of the tyre, and the turnup portions (6b₁) of the inner carcass ply (6A) extends into between the belt (7) and the carcass (6) so that the radially outer end (9c) thereof is secured therebetween. The sidewall reinforcing layers include: an inside layer (9a) disposed axially inside the main portion (6a₁) of the inner ply (6A); a middle layer (9b) disposed between the main portion (6a₁) of the inner ply (6A) and the main portion (6a₂) of the outer ply (6B); and an outside layer (9c) disposed axially outside the main portion of the outer ply (6a₂). At least one of the sidewall reinforcing rubber layers (9a, 9b, 9c) has a radially outer end located beneath the belt (7). At least one of the sidewall reinforcing rubber layers has a radially inner end located radially outwards of the bead core (5) but radially inwards of a maximum tyre section width point (M). At the maximum tyre section width point (M), the total of the thicknesses of the inside layer, middle layer and outside layer is not less than 50 % of the total thickness of the sidewall portion.

Fig.1



Description

[0001] The present invention relates to a pneumatic tyre, more particularly to a run-flat tyre having an improved sidewall reinforcing structure.

[0002] In order to improve run-flat performance such as the run-flat distance of a pneumatic tyre, as shown in Fig. 4, a tyre which has a sidewall portion (s) reinforced with a relatively thick rubber layer (g) has been proposed, wherein this thick rubber layer (g) is disposed on the axially inside of the carcass to extend along the inside of the tyre.

[0003] In this reinforcing structure, however, under run-flat conditions, damage starting from the carcass ply turnup edge (f1) is liable to occur as the edge (f1) is positioned in the sidewall portion, especially when it is positioned around the maximum tyre section width point. Further, the rubber layer (g) has a maximum thickness at the maximum tyre section width point. Under flat conditions, however, bending deformation becomes larger in the tyre shoulder portion than the maximum tyre section width portion. In other words, the bending is deformation concentrated on the shoulder portion. Thus, in this structure, the tyre has a tendency to have a weak point in the shoulder portion.

[0004] Such drawbacks may be eliminated by for example covering the edge (f1) with an additional carcass ply and increasing the thickness of the rubber layer (g). However, other problems arise such as an increase in the tyre weight and deterioration of ride comfort and dynamic performance under normal conditions.

[0005] It is therefore, an object of the present invention to provide a run-flat tyre improved in run-flat performance, e.g. running distance, durability and the like without increasing the tyre weight and deteriorating running performance under normal conditions.

[0006] According to one aspect of the present invention a run-flat tyre comprises a tread portion, a pair of sidewall portions, a pair of bead portions each with a bead core therein, a carcass comprising an inner ply and an outer ply each made of organic fibre cords, a belt disposed radially outside the carcass in the tread portion, sidewall reinforcing rubber layers disposed in each said sidewall portion, each of the inner ply and outer ply extending between the bead portions through the tread portion and sidewall portions and turned up around the bead core in each bead portion from the inside to the outside of the tyre to form a pair of turnup portion and a main portion therebetween wherein the turnup portions of the inner ply extended to between the belt and the carcass and each having a radially outer end secured therebetween, the sidewall reinforcing rubber layers including an inside layer disposed axially inside the main portion of the inner ply; a middle layer disposed between the main portion of the inner ply and the main portion of the outer ply; and an outside layer disposed axially outside the main portion of the outer ply, at least one of the sidewall reinforcing rubber layers having a radially outer end located beneath the belt, at least one of the sidewall reinforcing rubber layers having a radially inner end located radially outward of the bead core but radially inwards of a maximum tyre section width point, at the maximum tyre section width point, the total of the thicknesses of the inside layer, middle layer and outside layer being not less than 50 % of the thickness of the sidewall portion.

[0007] Preferably, the thickness of the sidewall portion at a point at 75 % of the tyre section height is 1.0 to 1.2 times the thickness of the sidewall portion at the maximum tyre section width point. The total of the thicknesses of the inside layer, middle layer and outside layer is not less than 40 % of the thickness of the sidewall portion at a point at 75 % of the tyre section height.

[0008] Further, it is preferable that the outer end(s) of at least one, preferably two, more preferably three of the reinforcing rubber layers is(are) disposed in a region beneath the breaker belt. It is preferable that the inner end(s) of at least one, preferably two, more preferably three of the reinforcing rubber layers is(are) disposed in a region radially inwards of the maximum tyre section width point but radially outwards of the radially outside of the bead core, and it is more preferable that both the outer and inner ends of at least one of the reinforcing rubber layers are disposed in the above-mentioned two regions.

[0009] An embodiment of the present invention will now be described in detail in conjunction with the accompanying drawings:

Fig.1 is a cross sectional view of an embodiment of the present invention;

Fig.2 is an enlarged cross sectional view of a shoulder portion thereof;

Fig.3 shows cross sections of the tyre under a normal condition and a flat condition obtained by a CT scanner; and

Fig.4 is a cross sectional view of a prior art tyre.

[0010] In the drawings, the run-flat tyre 1 according to the present invention comprises a tread portion 2, a pair of sidewall portions 3, a pair of bead portions 4 each with a bead core 5 therein, a radial ply carcass 6, a belt 7, 10 disposed radially outside the carcass 6 in the tread portion 2, and sidewall reinforcing layers 9 disposed in each of the sidewall portions 3.

[0011] In Fig.1, the tyre 1 is mounted on its standard wheel rim J and inflated to standard inner pressure but loaded with no tyre load. The sizes or dimensions of the tyre are measured under this condition if not specifically mentioned. Here, the standard rim is the "standard rim" specified in JATMA, the "Measuring Rim" in ETRTO, the "Design Rim" in

TRA or the like. The standard pressure is the "maximum air pressure" in JATMA, the "Inflation Pressure" in ETRTO, the maximum pressure given in the "Tyre Load Limits at Various Cold Inflation Pressures" table in TRA or the like. The standard load is the "maximum load capacity" in JATMA, the "Load Capacity" in ETRTO, the maximum value given in the above-mentioned table in TRA or the like. In case of passenger car tyres, however, as the standard pressure, 180 kPa is used.

[0012] The carcass 6 comprises an inner ply 6A and an outer ply 6B each made of organic fibre cords. For the organic fibre cords, rayon cords are used in this embodiment, but other materials such as polyester, nylon and the like can be used. The cords of each carcass ply are arranged radially at an angle of 75 to 90 degrees with respect to the tyre equator C so that the ply has a radial structure. In this embodiment, the cord angle in each ply is the same value of about 88 degrees but the inclining directions are opposite with respect to the tyre equator C. Thus, the cords of one ply cross those of the other ply at a small angle of about 4 degrees in this example.

[0013] The belt includes a breaker 7 and a band or bandage 10 disposed radially outside the breaker 7.

[0014] The breaker 7 comprises two crossed plies 7A and 7B, each ply made of parallel cords laid at an angle of from 10 to 35 degrees with respect to the tyre equator C. In this embodiment, each ply is made of aramid cords laid at 22 degrees. Aside from aramid cords, steel cords and the like can be used.

[0015] The band 10 is made of an organic fibre cord laid substantially parallel to the tyre circumferential direction. The band cords have a lower elastic modulus than the breaker cords.

[0016] In this embodiment, the band 10 is composed of a pair of axially spaced edge-band plies 10A covering the axial edges of the breaker 7 and a full-width band ply 10B disposed radially outside thereof and extending across the substantially full width of the breaker 7.

[0017] Preferably, each edge-band ply 10A has a width of about 10 to 20 % (in this example about 16%) of the axial width 3W of the breaker 7.

[0018] Both the band plies 10A and 10B in this embodiment are formed by spirally winding a tape of rubber, in which parallel nylon cords are embedded along the length thereof.

[0019] By using such a spiral band 10, it becomes possible to effectively prevent ply separation failure even if the tread portion 2 warps as shown in Fig.3 by a chain line. Thus, the durability under run-flat condition can be improved.

[0020] According to the present invention, the above-mentioned carcass plies 6A and 6B extend between the bead portions through the tread portion and sidewall portions and are turned up around the bead core 5 in each bead portion from the inside to the outside of the tyre so that: the carcass ply 6A comprises a pair of turnup portions 6b1 and a main portion 6a1 therebetween; and the carcass ply 6B comprises a pair of turnup portions 6b2 and a main portion 6a2 therebetween.

[0021] The edges 6e of the turnup portions 6b1 of the inner ply 6A extend to between the carcass 6 and breaker 7, and the overlap 11 of the turnup portion 6b1 with the breaker 7 has an axial length L of from 3 to 8 % (in this embodiment about 6.5%) of the axial width BW of the breaker.

[0022] The turnup portion 6b2 of the outer ply 6B has a height of about 0.4 to 0.6 times the tyre section height H (in this embodiment about 0.46 times) each from the bead base line BL. This means that the turnup end is positioned around the maximum tyre section width point M.

[0023] Incidentally, the tyre section height H is the radial height measured from the bead base line BL to the radially outermost point. The bead base line is an axial line passing to a position corresponding to the rim diameter.

[0024] In each of the above-mentioned bead portions 4, a bead apex 12 is disposed between the turnup portion 6b2 and main portion 6a2 of the outer carcass ply 6B. The bead apex 12 is made of a hard rubber and extends and tapers radially outwardly from the outside 5a of the bead core 5.

[0025] The above-mentioned sidewall reinforcing layers 9 include: an inside reinforcing rubber layer 9a disposed between the main portion 6a1 of the inner ply 6A and an air tight inner liner (i) disposed along the inside of the tyre; a middle reinforcing rubber layer 9b disposed between the main portions 6a1 and 6a2 of the inner and outer plies 6A and 6B; and an outside reinforcing rubber layer 9c disposed between the main portion 6a2 of the outer ply 6B and the turnup portions 6b1 and 6b2. Each of the reinforcing rubber layers 9a-9c tapers radially inwardly and radially outwardly.

[0026] In this embodiment, each layer (9a, 9b, 9c) has a radially outer end (9a1, 9b1, 9c1) located beneath, i.e. radially inwards of, the breaker 7 as shown in Fig.2, and a radially inner end (9a2, 9b2, 9c2) located radially inside the maximum tyre section width point M but radially outside the outer end 5a of the bead core 5.

[0027] The outer ends 9a1, 9b1 and 9c1 are placed at different axial positions so that the total thickness of the layers gradually changes from the tread portion 2 to the sidewall portion 3. In this embodiment, the outer end 9a1 is inmost, and the outer end 9c1 is outmost. Thus, the outer end 9b1 is in the middle of the others.

[0028] At least one of the radially inner ends 9a2, 9b2 and 9c2 of the reinforcing rubber layers 9a, 9b and 9c is positioned radially inwards of the maximum tyre section width point M. None of the radially inner ends 9a2, 9b2 and 9c2 is positioned radially inwards of the outer end 5a of the bead core 5.

[0029] In this embodiment shown in Fig.1, the radially inner tapered portion of the outside layer 9c and the radially outer tapered portion of the bead apex 12 are spliced, and in this spliced portion, the outside layer 9c is positioned

axially outside the bead apex 12 and the radially inner end 9c2 thereof reaches near the radially outside of the bead core 5.

[0030] On the other hand, the radially inner ends 9b2 and 9a2 of the middle and inside layers 9b and 9a reach to radially different positions which are radially inwards of the radially outer end of the bead apex 12 but radially outwards of the radially out end 5a of the bead core 5.

[0031] As shown in Fig.2, the total thickness of the sidewall portion 3 is such that the total thickness S2 at a point B is set in the range of from 1.0 to 1.4 times, preferably more than 1.0 times but not more than 1.4 times, more preferably more than 1.0 times but not more than 1.2 times, still more preferably 1.1 to 1.2 times the total thickness S1 at the maximum tyre section width point M.

[0032] The point B is a point on the outer surface of the tyre at a radial height of 75 % of the tyre section height H. The total thickness S1, S2 is measured along the normal direction to the outer surface or profile of the tyre.

[0033] At the maximum tyre section width point M, the total (a1+b1+c1) of the thicknesses a1, b1 and c1 of the layers 9a, 9b and 9c, respectively, is set to be not less than 50 %, preferably 50 to 70 %, more preferably 50 to 65 %, still more preferably 55 to 65 % of the total thickness S1.

[0034] Further, at the above-mentioned point B, the total (a2+b2+c2) of the thicknesses a2, b2 and c2 of the layers 9a, 9b and 9c, respectively, is set to be not less than 40 %, preferably 45 to 60 % of the total thickness S2.

[0035] Preferably, the total (a2+b2+c2) is smaller than the total (a1+b1+c1).

[0036] At the maximum tyre section width point M, it is preferable that the layers 9a, 9b and 9c are substantially the same thickness (a1=b1=c1). But, the following relationships may be possible: $a1 < b1 < c1$; $a1 > b1 > c1$; $a1 > b1 < c1$; $a1 < b1 > c1$.

[0037] Each of the reinforcing rubber layers 9 is made of a rubber compound of low-heat-generation having a complex elastic modulus E* of from 7.0 to 12.0 MPa and a loss tangent (tan δ) of not more than 0.02, preferably not more than 0.01, more preferably in the range of from 0.008 to 0.001.

[0038] In this embodiment, all the layers 9a, 9b and 9c are made of the same rubber compound, but it is also possible to use different rubber compounds which satisfy

$$E^*a > E^*b > E^*c \text{ or}$$

$$E^*a < E^*b < E^*c \text{ or}$$

$$E^*a < E^*b > E^*c \text{ or}$$

$$E^*a > E^*b < E^*c,$$

wherein E*a, E*b and E*c are the complex elastic moduli of the layers 9a, 9b and 9c, respectively.

[0039] If the complex elastic modulus E* is outside the range of from 7.0 to 12.0 MPa, the bending rigidity of the sidewall portion 3 tends to decrease and heat generation increases and ride comfort deteriorates.

[0040] If the loss tangent (tan δ) is more than 0.02, heat generation increases and the sidewall is liable to be broken by built-up heat.

Running speed: 100 km/h (straight), 50 km/h (150R and 110R corners)

Rim size: 16X7JJ (standard rim)

Tyre load: 580 kgf

[0041] The results are indicated by an index based on the Prior Art tyre being 100. The larger the index, the longer the runable distance.

[0042] From the test results, it was confirmed that the Example tyres were remarkably increased in runable distance although the tyre weight was maintained at the same level as the Prior Art tyre.

[0043] Fig.3 shows cross-sections of the Embodiment tyre when loaded with 4.41 kN under normally inflated condition (solid line) and a flat condition (chain line). This shows that even when the tyre is punctured the Embodiment tyre can endure its load without parts of the inner surfaces touching.

Table 1

Tyre	Prior	Ex.1	Ex.2	Ref.	Ex.3	Ex.4
	Fig.4	Fig.1	Fig. 1	Fig. 1	Fig. 1	Fig. 1
Carcass cord	rayon 1840 dtex/2					
Breaker cord	aramid 1670 dtex/2					
Band cord	nylon 1400 dtex/2					

Table 1 (continued)

Reinforcing rubber layers Complex elastic modulus Loss tangent						
	9.2 MPa		inside=middle=outside= 9.2 MPa			
	0.005		inside=middle=outside= 0.005			
S1 (mm)	20	18	18	15	18	18
a1+b1+c1 (mm)	-	10	10	7	10	10
(a1+b1+c1)/S1	-	0.56	0.56	0.46	0.56	0.56
S2 (mm)	18	20	17	17	20	24
a2+b2+c2 (mm)	-	9	7	7	7	12
(a2+b2+c2)/S2	-	0.45	0.41	0.41	0.35	0.5
S2/S1	0.9	1.11	0.94	1.13	1.11	1.33
Run-flat performance	100	300	100	50	150	400
Tyre weight	100	100	95	80	100	110

Claims

1. A run-flat tyre comprising a tread portion (2), a pair of sidewall portions (3), a pair of bead portions (4) each with a bead core (5) therein, a carcass (6) comprising an inner ply (6A) and an outer ply (6B) each made of organic fibre cords, a belt (7) disposed radially outside the carcass (6) in the tread portion (2), characterised by sidewall reinforcing rubber layers (9) disposed in each said sidewall portion (3), each of the inner ply (6A) and outer ply (6B) extending between the bead portions (4) through the tread portion (2) and sidewall portions (3) and turned up around the bead core (5) in each said bead portion (4) from the inside to the outside of the tyre to form a pair of turnup portions (6b₁, 6b₂) and a main portion (6a₁, 6b₂) therebetween, the turnup portions of the inner ply extended into between the belt (7) and the carcass (6) and each having a radially outer end (6e) secured therebetween, said sidewall reinforcing rubber layers (9) including an inside layer (9a) disposed axially inside the main portion (6a₁) of the

3. A run-flat tyre according to claim 1 or 2, characterised in that the total of the thicknesses (a₁, b₁, c₁) of the inside layer, middle layer and outside layer is not less than 40 % of the thickness S2 of the sidewall portion at a point at 75 % of the tyre section height.

4. A run-flat tyre according to claim 1, 2 or 3, characterised in that the radially outer ends (9a, 9b, 9c) of the inside, middle and outside layers (9a, 9b, 9c) are disposed in a region beneath the breaker belt (7).

5. A run-flat tyre according to any of claims 1 to 4, characterised in that the radially inner ends (9a₂, 9b₂, 9c₂) of the inside, middle and outside layers (9a, 9b, 9c) are disposed in a region radially inwards of the maximum tyre section width point (M) but radially outwards of the radially outer end of the bead core (5).

Fig.1




Fig.2




Fig.3




Fig.4

